

CF1-3800

Thermally conductive fluorosilicone elastomer

DESCRIPTION

- A two-part, thixotropic compound
- 15:1 Mix Ratio (Part A:B)
- Provides thermal conductivity when cured
- Cures at room or temperature or rapidly with heat

APPLICATION

- Provides heat transfer between electrical/electronic components and heat sinks
- For use as a sealant, adhesive or molding material requiring solvent resistance
- Use to adhere covers on housings or where grooves or other configurations require a non-flowable material
- For applications requiring an operating temperature range of -65°C to 225°C (-85°F to 437°F)

PROPERTIES

Typical Properties	Average Result	Metric Conv.	Standard	NT-TM
Uncured:				
Appearance, Part A	White	-	ASTM D2090	002
Appearance, Part B	Translucent	-	ASTM D2090	002
Consistency	Paste	-	-	-
Work Time	90 min	-	-	008
Cured: 30 minutes at 150°C (302°F)				
Specific Gravity	1.53	-	ASTM D792	003
Durometer, Type A	50	-	ASTM D2240	006
Tensile Strength	125 psi	0.86 MPa	ASTM D412	007
Elongation	50%	-	ASTM D412	007
Thermal Conductivity	30 x 10 ⁻⁴ cal/cm-sec°C	1.25 W/m-K	ASTM E1530	101

The above properties are tested on a lot-to-lot basis. Do not use as a basis for preparing specifications. Please [contact](#) NuSil Technology for assistance and recommendations in establishing particular specifications.

INSTRUCTIONS FOR USE

Mixing

Mix CF1-3800 Part A and Part B in a 15:1 mix ratio by weight. Ensure that the conductive filler is homogenous throughout the mixture.

Substrate Considerations

CF1-3800 will cure in contact with most materials common to electronic assemblies. Exceptions include: butyl and chlorinated rubbers, some RTV silicones and unreacted residues of some curing agents. Units being encapsulated or potted should be clean and free of surface contaminants. Containers and dispensers being used with CF1-3800 should also be clean and dry. Cure inhibition can usually be prevented by washing all containers with clean solvent or volatilizing the contaminants by heating.

Vacuum Deaeration

Remove air entrapped during mixing by common vacuum deaeration procedure, observing all safety precautions. Slowly apply vacuum to a container both rated for use and at least four times the volume of material being deaerated. Hold vacuum until the presence of air is no longer evident.

Adjustable Cure Schedule

Product cures at room temperature and a wide range of elevated temperatures and cure times to accommodate different production needs. Contact NuSil Technology for details.

SPECIFICATIONS

Do not use the properties shown in this technical profile as a basis for preparing specifications. Please [contact](#) NuSil Technology for assistance and recommendations in establishing particular specifications.

WARRANTY INFORMATION

The warranty period provided by NuSil Technology LLC (hereinafter "NuSil Technology") is 12 months from the date of shipment when stored below 40°C in original unopened containers. Unless NuSil Technology provides a specific written warranty of fitness for a particular use, NuSil Technology's sole warranty is that the product will meet NuSil Technology's then current specification. NuSil Technology specifically disclaims all other expressed or implied warranties, including, but not limited to, warranties of merchantability and fitness for use. The exclusive remedy and NuSil Technology's sole liability for

Packaging

100 Gram Kit
500 Gram Kit

Warranty

12 Months

breach of warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. NuSil Technology expressly disclaims any liability for incidental or consequential damages.

WARNINGS ABOUT PRODUCT SAFETY

NuSil Technology believes, to the best of its knowledge, that the information and data contained herein are accurate and reliable. The user is responsible to determine the material's suitability and safety of use. NuSil Technology cannot know each application's specific requirements and hereby notifies the user that it has not tested or determined this material's suitability or safety for use in any application. The user is responsible to adequately test and determine the safety and suitability for their application and NuSil Technology makes no warranty concerning fitness for any use or purpose. NuSil Technology has completed no testing to establish safety of use in any medical application.

NuSil Technology has tested this material only to determine if the product meets the applicable specifications. (Please [contact](#) NuSil Technology for assistance and recommendations when establishing specifications.) When considering the use of NuSil Technology products in a particular application, review the latest Material Safety Data Sheet and [contact](#) NuSil Technology with any questions about product safety information.

Do not use any chemical in a food, drug, cosmetic, or medical application or process until having determined the safety and legality of the use. The user is responsible to meet the requirements of the U.S. Food and Drug Administration (FDA) and any other regulatory agencies. Before handling any other materials mentioned in the text, the user is advised to obtain available product safety information and take the necessary steps to ensure safety of use.

PATENT / INTELLECTUAL PROPERTY WARNING

NuSil Technology disclaims any expressed or implied warranty against the infringement of any domestic or international patent/intellectual property right. NuSil Technology does not warrant the use or sale of the products described herein will not

infringe the claims of any domestic or international patent/intellectual property right covering the product itself, its

use in combination with other products, or its use in the operation of any process.